

ARTICLE

Received 12 Apr 2014 | Accepted 25 Aug 2014 | Published 30 Sep 2014

DOI: 10.1038/ncomms6064

Chiral superfluidity with p -wave symmetry from an interacting s -wave atomic Fermi gas

Bo Liu¹, Xiaopeng Li^{1,2}, Biao Wu^{3,4} & W. Vincent Liu^{1,5}

Chiral p -wave superfluids are fascinating topological quantum states of matter that have been found in the liquid $^3\text{He-A}$ phase and arguably in the electronic Sr_2RuO_4 superconductor. They are fundamentally related to the fractional $5/2$ quantum Hall state, which supports fractional exotic excitations. Past studies show that they require spin-triplet pairing of fermions by p -wave interaction. Here we report that a p -wave chiral superfluid state can arise from spin-singlet pairing for an s -wave interacting atomic Fermi gas in an optical lattice. This p -wave state is conceptually distinct from all previous conventional p -wave states as it is for the centre-of-mass motion, instead of the relative motion. It leads to spontaneous generation of angular momentum, finite Chern numbers and topologically protected chiral fermionic zero modes bounded to domain walls, all occurring at a higher critical temperature in relative scales. Signature quantities are predicted for the cold atom experimental condition.

¹Department of Physics and Astronomy, University of Pittsburgh, Pittsburgh, Pennsylvania 15260, USA. ²Condensed Matter Theory Center and Joint Quantum Institute, Department of Physics, University of Maryland, College Park, MD 20742, USA. ³International Center for Quantum Materials, School of Physics, Peking University, Beijing 100871, China. ⁴Collaborative Innovation Center of Quantum Matter, Beijing 100871, China. ⁵Department of Applied Physics, Zhejiang University of Technology, Hangzhou 310023, China. Correspondence and requests for materials should be addressed to W.V.L. (email: w.vincent.liu@gmail.com).

Topological superconductors, like the type of $p_x + ip_y$ -wave pairing studied in the liquid ^3He (ref. 1) and strontium ruthenates², are among the most desirable unconventional many-body states in condensed matter physics³. In two dimensions (2Ds), their topological properties are fundamentally linked to a class of fractional quantum Hall states of non-Abelian statistics⁴. Studies of vortices in such materials point to fascinating braiding statistics and applications in topological quantum computing. The fate of topological superconductivity in 2D electronic matter remains, however, debatable. In the field of ultracold atoms, this phase was predicted to appear near the p -wave Feshbach resonance in Fermi gases⁵. However, the life time of such systems is severely limited by the three-body collisions, and achieving superfluidity in the resonance regime was found experimentally challenging⁶. Creating the equivalent of p -wave interactions using spin-orbit coupling or dipolar interactions provides a different interesting approach^{7,8}, for which future experimental breakthroughs are desired to suppress heating or ultracold chemical reactions. Another approach proposed to get around⁹ is to hybridize materials of topological and superconducting properties. This approach nevertheless requires advanced material engineering. After all, the search for chiral p -wave superconductivity in 2Ds has stood largely open for both electronic and atomic matter systems.

Here we report the discovery of a new mechanism to achieve chiral topological superfluidity. We shall introduce this with a specific model of cold fermionic atoms in an optical lattice, to be described below. The key idea is a centre-of-mass p -wave superconducting pairing. Unlike the past models that require a p -wave two-body interaction or induced ones^{10–18}, the present pairing mechanism departs from the conventional reliance on p -wave pairing in relative motion. Here the pairing of fermions takes place between s and p orbitals, which have even and odd parity, respectively. Recently, the research of higher orbital bands in optical lattices has evolved rapidly¹⁹, where the orbital degrees of freedom are found to play a crucial role as in solid-state materials. From the early experimental attempt²⁰ to the breakthrough observation²¹ of long-lived p -band bosonic atoms in a checkerboard lattice, a growing evidence points to an exotic $p_x + ip_y$ orbital Bose–Einstein condensate¹⁹. For fermions studied in this work, the decay from higher to lower bands is prevented by Pauli blocking, and the fermionic p -band system is even more robust than the bosonic counterpart. Concerning p -band fermions with attractive interaction, superfluid states similar to the type of Fulde–Ferrell–Larkin–Ovchinnikov were found in the theoretical studies of pairing within the p -bands²² and that between the s -band and a single p -band²³. As we shall show with the model below, pairing fermions from the orbitals of different angular momenta can lead to other unexpected results.

Results

Effective model. Let us consider an attractive s -wave-interacting Fermi gas composed of two hyperfine states, to be referred to as spin \uparrow and \downarrow , loaded in a spin-dependent 2D optical lattice shown in Fig. 1a. The spin dependence of the lattice is motivated by various theoretical designs^{24,25} and most importantly the recent experimental demonstration of it with bosons^{26,27}. Further, let the gas be tuned with a population imbalance between the two spin species by the techniques developed in the recent experimental advances^{28–30}. A key condition that we propose here is to tune the population imbalance (or equivalently the chemical potential difference) sufficiently large such that the spin \uparrow and \downarrow Fermi levels reside in the s and p orbital bands, respectively. The rotation symmetry (C_4) of the lattice dictates that the two p orbital bands, p_x and p_y , are degenerated at the high symmetry points in the momentum space. Later on we shall see that this symmetry and

hence degeneracy are necessary for the $p_x + ip_y$ -wave paired superfluidity. Technically speaking, the Bravais lattices for the spin up and down fermions are 45° rotated from each other.

A system of fermionic atoms, say ^6Li , loaded into an optical lattice (Fig. 1a) in the tight binding regime is described by a multi-orbital Fermi Hubbard model

$$H = H_0 + H_{\text{int}}, \quad (1)$$

where H_0 describes tunnelling pictorially represented in Fig. 1b,c (the expression for H_0 is standard and is given in Supplementary Note 1) and H_{int} is the Hubbard interaction,

$$H_{\text{int}} = -U \sum_{\mathbf{R}} [C_s^\dagger(\mathbf{R})C_s(\mathbf{R}) - \frac{1}{2} [C_{p_x}^\dagger(\mathbf{R})C_{p_x}(\mathbf{R}) + C_{p_y}^\dagger(\mathbf{R})C_{p_y}(\mathbf{R}) - 1]]. \quad (2)$$

Here $C_v^A(\mathbf{R})$ is a fermionic annihilation operator for the localized v (s , p_x or p_y) orbital on A sites and the corresponding annihilation operator on the B sites is denoted as $C_v^B(\mathbf{R})$ with \mathbf{R} labels the lattice site. The interactions between s and p orbitals originate from interactions between two hyperfine states, which are tunable by the s -wave Feshbach resonance in ultracold atomic gases. We focus on the case with attractive interaction where superconducting pairing is energetically favourable. Although the annihilation operators $C_v^B(\mathbf{R})$ do not appear in the interaction H_{int} , they play important roles in the tunnelling Hamiltonian H_0 by determining the orientation of Fermi surfaces. With spin \downarrow fermions residing on both A and B sites, and spin \uparrow once on A sites only, Fermi surfaces of the s -band for spin \uparrow and the p -band for spin \downarrow are approximately two squares right on top of each other. Such a momentum-space geometry leads to nearly perfect Fermi surface nesting, which is the key to the p -wave superconducting pairing between s and p orbitals at weak interaction.

The system, as described by the Hamiltonian in equation (1), exhibits lattice rotation C_4 and reflection symmetries. For the reflection in the horizontal and vertical direction (see Fig. 1a), the fermionic operators transform as $\mathcal{R}_{\parallel} \equiv \{C_{p_x}^{A/B}(\mathbf{R}) \rightarrow -C_{p_x}^{A/B}(-R_y, -R_x), C_{p_y}^{A/B}(\mathbf{R}) \rightarrow C_{p_y}^{A/B}(-R_y, -R_x)\}$ and $\mathcal{R}_{\perp} \equiv \{C_{p_x}^{A/B}(\mathbf{R}) \rightarrow C_{p_x}^{A/B}(R_y, R_x), C_{p_y}^{A/B}(\mathbf{R}) \rightarrow -C_{p_y}^{A/B}(R_y, R_x)\}$, respectively. Under the lattice rotation, $C_{p_x}^{A/B}(\mathbf{R}) \rightarrow C_{p_y}^{A/B}(-R_y, R_x)$, $C_{p_y}^{A/B}(\mathbf{R}) \rightarrow -C_{p_x}^{A/B}(-R_y, R_x)$. These symmetries, reflection symmetries in particular, play an essential role in the following theory.

Ginzburg–Landau theory. From the analysis of Cooper’s problem (see Supplementary Note 2 and Supplementary Fig. 1), we conclude that condensation of Cooper pairs at $\mathbf{Q} = (\pi/a, \pi/a)$ is most energetically favourable in the ground state, where a is the lattice constant. This peculiar momentum selection for Cooper pairs is related to the Fermi surface nesting at half-filling. Then, it is convenient to introduce two slowly varying bosonic fields $\Delta_x(\mathbf{x})$ and $\Delta_y(\mathbf{x})$, which represent Cooper pairs $(-1)^{R_x+R_y} U \langle C_{p_y}^A(\mathbf{R})C_s^A(\mathbf{R}) \rangle$ and $(-1)^{R_x+R_y} U \langle C_{p_x}^A(\mathbf{R})C_s^A(\mathbf{R}) \rangle$ in the low-energy limit, respectively, with \mathbf{x} a coarse grained coordinate for the lattice labelling \mathbf{R} . The pairing fields $\Delta_x(\mathbf{x})$ and $\Delta_y(\mathbf{x})$ are parity odd and transform as $\Delta_x(x, y) \rightarrow -\Delta_x(-y, -x)$, $\Delta_y(x, y) \rightarrow \Delta_y(-y, -x)$ and $\Delta_x(x, y) \rightarrow \Delta_x(y, x)$, $\Delta_y(x, y) \rightarrow -\Delta_y(y, x)$ under reflection in the horizontal and vertical directions (see Fig. 1a), respectively. The symmetry of the pairing fields plays a crucial role in determining the form of the free energy, to be demonstrated in the following. A two-flavour Ginzburg–Landau free energy respecting all the symmetries is given as follows

$$F[\Delta_x, \Delta_y] = \int d^2\mathbf{x} [f_{\text{Mean}}(\mathbf{x}) + f_{\text{Gaussian}}(\mathbf{x})], \quad (3)$$




Figure 1 | Optical lattice system and zero-temperature phase diagram. (a) Schematic picture of a 2D spin-dependent optical lattice, where the spin up (*s* orbital band) and down (*p* orbital band) component lying within different geometry lattice potential, respectively. Here *A* and *B* stand for two different sites in one unit cell, \vec{e}_x and \vec{e}_y are the primitive unit vectors. (b and c) Schematic views illustrate tunnelling t_0 , t_1 , t_2 and t_3 of fermions prepared in the *s* and *p* orbitals, respectively. (d) Zero-temperature phase diagram when $t_1/t_0 = 8$, $t_2/t_0 = 2$ —The solid line illustrates the phase transition from normal gas (NG) to superfluid state (SF). When $U/t_0 < 7$, the critical value of t_3/t_0 as shown by the dash line, beyond this threshold a phase transition from $p_x \pm p_y$ to $p_x \pm ip_y$ superfluid state occurs. When $U/t_0 \geq 7$, $p_x \pm ip_y$ superfluid state is the ground state with non-zero t_3 . The thick solid line stands for a two-component superfluid state. (e and f) Pictorially illustrate the distinction between centre-of-mass and conventional $p + ip$ pairings. Here, the character of $p + ip$ pairing states is demonstrated by the phase of the superconducting gap labelled by the colour of the torus. In e, the Cooper pair is a spin-singlet pair composed of two spin species fermions and has finite centre-of-mass orbital angular momentum, whereas in f it is a conventional spin-triplet pair formed by single species fermions and has conventional relative motion angular momentum.

with $f_{\text{Mean}} = r(|\Delta_x|^2 + |\Delta_y|^2) + g_1(|\Delta_x|^4 + |\Delta_y|^4) + g_2|\Delta_x|^2|\Delta_y|^2 + g_3(\Delta_x^*\Delta_y^*\Delta_x\Delta_y + h.c.)$ and $f_{\text{Gaussian}} = K(|\partial_x\Delta_x|^2 + |\partial_y\Delta_y|^2 + |\partial_x\Delta_y|^2 + |\partial_y\Delta_x|^2)$. Here r , g_1 , g_2 , g_3 and K are phenomenological coefficients to be related to the Hamiltonian (equation (1)) by microscopic calculations.

This free energy generalizes the theory of two-gap superconductivity as proposed in the context of transition metals³¹. We have neglected temporal fluctuations of Cooper pair fields and such a treatment is valid at non-zero temperature away from quantum critical regime. In this theory, we want to emphasize two key points owing to the reflection symmetries: first, Δ_x and Δ_y are decoupled at quadratic level; second, linear derivatives such as $\Delta_x^*\partial_x\Delta_x + \Delta_x^*\partial_y\Delta_x$ are prohibited. The absence of linear derivatives makes modulations in $\Delta_{x,y}$ suppressed, and condensation of Cooper pairs at $(\pi/a, \pi/a)$ is expected to be stable against weak perturbations such as having small t_2 (Fig. 1c) or slightly doping away from half-filling. For finite t_2 and t_3 (Fig. 1c), the stability (that is, $K > 0$ in equation (3)) is confirmed in our numerics (see Supplementary Note 3 and Supplementary Figure 2). The rotation symmetry plays another key role. For example, it protects the degeneracy of the two components Δ_x and Δ_y , that is, the splitting terms such as $|\Delta_x|^2 - |\Delta_y|^2$ are not allowed in the free energy. In short, the point group D_4 symmetry protects the form of the free energy in equation (3). Here we point out that the preserved space lattice rotation symmetry makes our model different from the spin-orbit-coupled systems, where such symmetry is absent.

With the phenomenological coefficients r and g_3 obtained from integrating out fermions (see Supplementary Fig. 2), we find a phase diagram shown in Fig. 1d. With moderate attraction $U < 7t_0$, a first-order phase transition from the $p_x \pm p_y$ to $p_x \pm ip_y$ phase occurs when the diagonal hopping t_3 is above some critical value. Surprisingly, when the attraction is strong enough $U > 7t_0$, we find that even infinitesimal t_3 makes the $p_x \pm ip_y$ favourable, opening a wide window for this non-trivial state. When $t_3 = 0$, the system has $U(1) \times U(1)$ symmetry, which means no phase coherence between the two components Δ_x and Δ_y . We also find that the superconducting gaps Δ_x and Δ_y have anisotropy in momentum space (see Supplementary Note 5 and Supplementary

Fig. 4). Here we emphasize the crucial role of t_3 in determining the relative phase between Cooper pairs Δ_x and Δ_y . As it mixes the p_x and p_y orbitals, the particle numbers of these two orbitals are no longer separately conserved, and will consequently lock the relative phase between these two pairing fields. For large t_3 , the $p_x \pm ip_y$ state mostly minimizes the free energy and becomes energetically favourable. Surprisingly, this $p_x \pm ip_y$ phase is found to occupy a large region in the phase diagram (Fig. 1d). In the strong interaction regime, Cooper pairs behave like tightly bound repulsive molecules and the energetic selection of the $p_x \pm ip_y$ phase can be understood from an analogue of Hund's rule for *p*-orbital bosons³², where maximizing the angular momentum generically saves the interaction energy cost.

The *p*-wave superfluidity proposed here refers to a centre-of-mass *p*-wave pairing state. The distinction of such pairing from the conventional spin-triplet pairing $p_x + ip_y$ states is illustrated in Fig. 1e,f. To further distinguish this state from the conventional relative *p*-wave pairing that usually involves two different sites (for example, pairs between spinless fermions) owing to the fermionic statistics, we consider a general pairing form $\Phi_{\text{COM}}(\mathbf{x}, \mathbf{x}')$, which represents the Cooper pair between parity even and odd orbitals (that is, *s* and *p* orbitals) from any two sites. Under parity transformation, the pairing transforms as $\Phi_{\text{COM}}(\mathbf{x}, \mathbf{x}') \rightarrow -\Phi_{\text{COM}}(-\mathbf{x}, -\mathbf{x}')$, rather than $\Phi_{\text{COM}}(\mathbf{x}, \mathbf{x}') \rightarrow -\Phi_{\text{COM}}(\mathbf{x}', \mathbf{x})$, which distinguishes the centre-of-mass from the conventional relative *p*-wave pairing. A remarkable feature immediately borne out of this pairing mechanism is the centre-of-mass *p*-wave superfluidity arises directly from a purely *s*-wave two-body interaction, requiring neither engineered *p*-wave interactions nor induced effective ones. This leads to a significantly improved transition temperature, which is confirmed by our study of the finite temperature phase transitions for the model Hamiltonian (equation (1); see Supplementary Note 4 and Supplementary Figure 3). For example, taking a typical density of the ⁴⁰K gas^{33,34} and the potential depths of the optical lattice to be $V_s/E_R = 3$ and $V_p/2E_R = 5$ for *s* and *p* orbitals (see the lattice potentials in Methods), respectively, we estimate the Kosterlitz–Thouless transition temperature can reach around 100 nK or higher, being within the experimental temperature scope³⁵.

Gapless chiral fermions. We now show that the $p_x \pm ip_y$ superfluid state possesses important measurable signatures because of the broken time reversal Z_2 symmetry, which belongs to the Ising universality class. Following the standard procedure, our calculation finds that the state is topologically nontrivial by a non-zero Chern number, which is 1 and -1 for the $p_x + ip_y$ and $p_x - ip_y$ state, respectively. The topological properties are manifested in the existence of gapless chiral fermions, emergent on a domain wall connecting topologically distinct regions. In experiments, Ising domains of $p_x + ip_y$ and $p_x - ip_y$ are expected to spontaneously form as have been observed in the recent cold atom experiment studying ferromagnetic transitions³⁶. In the following, we show that a domain wall defect carrying gapless fermions as bounded surface states is experimentally accessible.

Considering a lattice geometry in the presence of a domain wall decorated superconducting background as in Fig. 2a, the mean-field Hamiltonian is given by

$$\begin{aligned}
 H_M = & H_0 - U \sum_{\mathbf{R}} [C_s^{A\dagger}(\mathbf{R}) C_{p_x}^{A\dagger}(\mathbf{R}) \langle C_{p_x}^A(\mathbf{R}) C_s^A(\mathbf{R}) \rangle \\
 & + \langle C_s^{A\dagger}(\mathbf{R}) C_{p_x}^{A\dagger}(\mathbf{R}) \rangle C_{p_x}^A(\mathbf{R}) C_s^A(\mathbf{R}) \\
 & + C_s^{A\dagger}(\mathbf{R}) C_{p_y}^{A\dagger}(\mathbf{R}) \langle C_{p_y}^A(\mathbf{R}) C_s^A(\mathbf{R}) \rangle \\
 & + \langle C_s^{A\dagger}(\mathbf{R}) C_{p_y}^{A\dagger}(\mathbf{R}) \rangle C_{p_y}^A(\mathbf{R}) C_s^A(\mathbf{R})] \\
 & + U \sum_{\mathbf{R}} \{ C_s^{A\dagger}(\mathbf{R}) C_s^A(\mathbf{R}) + \frac{1}{2} [C_{p_x}^{A\dagger}(\mathbf{R}) C_{p_x}^A(\mathbf{R}) \\
 & + C_{p_y}^{A\dagger}(\mathbf{R}) C_{p_y}^A(\mathbf{R})] \}.
 \end{aligned} \quad (4)$$

Here we emphasize that the centre-of-mass p -wave superfluidity, as described in equation (4), exhibits an unbroken spin $U(1)$ symmetry under the transformation $C_s^A \rightarrow e^{i\theta} C_s^A$ and $C_{p_x/y}^A \rightarrow e^{-i\theta} C_{p_x/y}^A$. Such an unbroken continuous symmetry is

absent in the conventional relative p -wave pairing state for either spinless or spin-orbit-coupled fermion systems. The energy spectrum of fermionic excitations is obtained by diagonalizing equation (4). With the periodical boundary condition chosen in the x direction (Fig. 2a), the momentum k_x is a good quantum number and the energy spectra in Fig. 2b is thus labelled by k_x . For the same reason as in quantum Hall insulators, the number of gapless chiral modes moving along the interface is topologically determined by the difference of the Chern numbers in regions on either side of the interface³⁷; in this case, $|\Delta C| = 2$. This conclusion is confirmed in our numerics. As shown in Fig. 2b, we find four gapless chiral modes, with two localized on the domain wall (purple colour) and the other two on the outer edges of the lattice (red colour). From their spectra $\varepsilon_n(k_x)$, the two chiral modes on the domain wall have positive group velocities, which lead to anomalous mass flow along the domain wall³⁸.

Experimental signatures. Several different methods can be used to observe our proposed chiral p -wave superfluidity experimentally. For instance, one of the direct experimental evidence for this topological superfluids, as in quantum Hall insulators, is the existence of the gapless chiral edge states. The domain wall supporting gapless chiral fermions between two Ising domains $p_x + ip_y$ and $p_x - ip_y$ can spontaneously form in atomic gases in a trap. These gapless fermionic states lead to signatures in local density of states (LDOS), which can be measured by radio-frequency (RF) spectroscopy. The LDOS is calculated as $\rho(y, E) = 1/2 \sum_{n,v} \int dk_x [|u_n^v|^2 \delta(E - \varepsilon_n) + |v_n^v|^2 \delta(E + \varepsilon_n)]$, where $(u_n^v, v_n^v)^T$ is the eigenvector corresponding to the eigenenergy ε_n of Hamiltonian equation (4) and v runs over all the Wannier orbitals (s, p_x or p_y) on A and B sites. We find that these gapless modes manifest themselves by a peak in LDOS located at the position of the domain wall, as shown in Fig. 2c–e. The reason for that peak of LDOS is the existence of localized gapless surface




Figure 2 | Topological domain wall defect. (a) Schematic picture of a lattice system in the presence of a domain wall. (b) Energy spectrum of the system with a domain wall defect, when $t_1/t_0 = 8$, $t_2/t_0 = 2$, $t_3/t_0 = 0.1$ and $U/t_0 = 9$. The purple and red branches correspond to the modes at the domain wall and the edge of the lattice, respectively. (c–e) The local density of states (LDOS) defined in the main text. The peak of LDOS located at domain wall is shown by red colour in c and further shown with $E/t_0 = 0$ and $y/a = 49$ in d and e, respectively. The LDOS is in units of $1/at_0$.

states, reminiscent of the quantum Hall edge states. This spatially localized zero-energy peak in LDOS can be detected using spatially resolved RF spectroscopy technique³⁹. Taking a laser wavelength of $\lambda = 1,024$ nm typical for the current optical lattices, the width of the LDOS peak is estimated about $2\ \mu\text{m}$. This is greater than the reported spatial resolution (about $1.4\ \mu\text{m}$) in the current experimental RF measurement³⁹, which makes the detection of this signal experimentally accessible. Besides detecting edge properties, the bulk Chern number can also be used to demonstrate the topological nature of our proposed chiral p -wave superfluidity. For the detection of Chern numbers, one may adopt the existing proposals either from time-of-flight measurement^{40–43} or from Bloch oscillation technique^{44,45}.

Discussion

We now discuss the sharp distinction between our proposal to realize chiral p -wave superfluidity and that in previous studies^{10–18}. Our proposed chiral p -wave superfluid state is a centre-of-mass p -wave superconducting pairing state. That is fundamentally different from other conventional p -wave superfluidity in previous studies, where the pairing order parameter has p -wave symmetry in the relative motion. The conceptual difference leads to two major distinct features in centre-of-mass p -wave state. One is that our proposal requires neither spin-orbit coupling nor an induced second-order effective p -wave interaction, automatically avoiding the challenge of their experimental realization in atomic Fermi gases. The centre-of-mass p -wave superfluidity proposed here arises directly from a purely s -wave two-body interaction. Hence, a short-ranged contact interaction as widely implemented in cold gases should satisfy well. This also significantly improves the transition temperature. The other feature is that the centre-of-mass p -wave superfluidity predicted here exhibits some unbroken symmetries such as spin $U(1)$ symmetry and space lattice rotation symmetry. Such symmetries are absent in the conventional relative p -wave pairing state (for example, in spin-orbit-coupled fermion systems).

We would like to stress that although the spin dependence of the studied lattice potentials is important to support our p -wave superconductivity in the weak interaction region, such lattices potentially causing experimental challenges could be avoided by considering strong interactions such as the resonance (see in Methods). The key ingredient for topological properties to emerge is rather from mixing Wannier orbitals of opposite parities. The connection between topological superconductivity and insulating or semimetallic phases^{46,47} involving the idea of mixing parities remains an intriguing question for future research.

In summary, we find a topological p -wave superfluid state in a spin imbalanced atomic Fermi gas with an s -wave interaction. Its pairing symmetry and topological origin differ from the previously known superconducting or superfluid phases. The p -wave symmetry refers to the centre-of-mass motion, not to the relative motion as in the well-known ^3He superfluid. The appearance of chiral fermionic zero modes bounded to domain walls is predicted as a concrete experimental signature for this novel state.

After the submission of this manuscript, we became aware of a related paper⁴⁸, which puts forward an idea of generating p -wave interaction on the optical lattice.

Methods

Spin-dependent optical lattice. Experimentally, one may consider the existing proposals for realizing spin-dependent optical lattices^{24,25}. Alternatively, the recent progress in group-II (alkaline-earth-metal) atoms points to the possibility of achieving even greater tunability by using the ground 1S_0 and long-lived metastable

3P_0 atomic levels, taking advantage of the strong orbit dependence of AC Stark effect in such systems. This should in principle be able to make the lattices for different components being completely independent (so maximally spin-dependent lattice) by selection of the appropriate wavelengths²⁵. To be more specific, for the model presented here, we consider the lattice configurations for spin up (s orbital) and down (p orbital) fermions are $V_{\uparrow}(x, y) = -V_s[\cos^2(k(x+y)) + \cos^2(k(x-y))]$ and $V_{\downarrow}(x, y) = -V_p[\cos^2(kx) + \cos^2(ky)]$, respectively. Here $k = \frac{2\pi}{\lambda}$, V_s and V_p are the lattice strength, and λ is the wavelength of laser. The phase-stable lattices should in principle be realized through the phase control technique developed in recent experiments^{49,50}. It is worthwhile to note that this special lattice configuration is to make the Cooper pair favourable even when interaction is weak. However, with strong interactions as in the resonance regime, such special lattice is expected to be unnecessary. The reason is that when the strong pairing-induced energy gap is a significant fraction of or is even comparable to the band width, Fermi surface nesting is no longer important for pairing.

References

- Volovik, G. E. *The Universe in a Helium Droplet* (Oxford University Press, 2003).
- Kallin, C. Chiral p -wave order in Sr_2RuO_4 . *Rep. Prog. Phys.* **75**, 042501 (2012).
- Nayak, C., Simon, S. H., Stern, A., Freedman, M. & Das Sarma, S. Non-Abelian anyons and topological quantum computation. *Rev. Mod. Phys.* **80**, 1083–1159 (2008).
- Read, N. & Green, D. Paired states of fermions in two dimensions with breaking of parity and time-reversal symmetries and the fractional quantum hall effect. *Phys. Rev. B* **61**, 10267 (2000).
- Gurarie, V. & Radzihovsky, L. Resonantly paired fermionic superfluids. *Ann. Phys.* **322**, 2–119 (2007).
- Regal, C. A., Ticknor, C., Bohn, J. L. & Jin, D. S. Tuning p -wave interactions in an ultracold Fermi gas of atoms. *Phys. Rev. Lett.* **90**, 053201 (2003).
- Galitski, V. & Spielman, I. B. Spin-orbit coupling in quantum gases. *Nature* **494**, 49–54 (2013).
- Baranov, M. A., Dalmonte, M., Pupillo, G. & Zoller, P. Condensed matter theory of dipolar quantum gases. *Chem. Rev.* **112**, 5012–5061 (2012).
- Qi, X.-L. & Zhang, S.-C. Topological insulators and superconductors. *Rev. Mod. Phys.* **83**, 1057–1110 (2011).
- Williams, R. A. *et al.* Synthetic partial waves in ultracold atomic collisions. *Science* **335**, 314–317 (2012).
- Julia-Diaz, B., Graß, T., Dutta, O., Chang, D. E. & Lewenstein, M. Engineering p -wave interactions in ultracold atoms using nanoplasmonic traps. *Nat. Commun.* **4**, 2046 (2013).
- Efremov, D. V. & Viverit, L. p -wave Cooper pairing of fermions in mixtures of dilute Fermi and Bose gases. *Phys. Rev. B* **65**, 134519 (2002).
- Zhang, C., Tewari, S., Lutchyn, R. M. & Das Sarma, S. $p_x + ip_y$ Superfluid from s -wave interactions of Fermionic cold atoms. *Phys. Rev. Lett.* **101**, 160401 (2008).
- Sato, M., Takahashi, Y. & Fujimoto, S. Non-Abelian topological order in s -wave superfluids of ultracold Fermionic atoms. *Phys. Rev. Lett.* **103**, 020401 (2009).
- Sau, J. D., Lutchyn, R. M., Tewari, S. & Das Sarma, S. Generic new platform for topological quantum computation using semiconductor heterostructures. *Phys. Rev. Lett.* **104**, 040502 (2010).
- Lutchyn, R. M., Sau, J. D. & Das Sarma, S. Majorana Fermions and a topological phase transition in semiconductor-superconductor heterostructures. *Phys. Rev. Lett.* **105**, 077001 (2010).
- Oreg, Y., Refael, G. & von Oppen, F. Helical liquids and Majorana bound states in quantum wires. *Phys. Rev. Lett.* **105**, 177002 (2010).
- Alicea, J. Majorana fermions in a tunable semiconductor device. *Phys. Rev. B* **81**, 125318 (2010).
- Lewenstein, M. & Liu, W. V. Optical lattices: orbital dance. *Nat. Phys.* **7**, 101–103 (2011).
- Müller, T., Fölling, S., Widera, A. & Bloch, I. State preparation and dynamics of ultracold atoms in higher lattice orbitals. *Phys. Rev. Lett.* **99**, 200405 (2007).
- Wirth, G., Olschlager, M. & Hemmerich, A. Evidence for orbital superfluidity in the p -band of a bipartite optical square lattice. *Nat. Phys.* **7**, 147–153 (2011).
- Cai, Z., Wang, Y. & Wu, C. Stable Fulde-Ferrell-Larkin-Ovchinnikov pairing states in two-dimensional and three-dimensional optical lattices. *Phys. Rev. A* **83**, 063621 (2011).
- Zhang, Z., Hung, H.-H., Ho, C. M., Zhao, E. & Liu, W. V. Modulated pair condensate of p -orbital ultracold fermions. *Phys. Rev. A* **82**, 033610 (2010).
- Liu, W. V., Wilczek, F. & Zoller, P. Spin-dependent Hubbard model and a quantum phase transition in cold atoms. *Phys. Rev. A* **70**, 033603 (2004).
- Daley, A. Quantum computing and quantum simulation with group-II atoms. *Quantum Inf. Process.* **10**, 865–884 (2011).
- McKay, D. & DeMarco, B. Thermometry with spin-dependent lattices. *N. J. Phys.* **12**, 055013 (2010).
- Soltan-Panahi, P., Luhmann, D.-S., Struck, J., Windpassinger, P. & Sengstock, K. Quantum phase transition to unconventional multi-orbital superfluidity in optical lattices. *Nat. Phys.* **8**, 71–75 (2012).

28. Zwierlein, M. W., Schirotzek, A., Schunck, C. H. & Ketterle, W. Fermionic superfluidity with imbalanced spin populations. *Science* **311**, 492–496 (2006).
29. Partridge, G. B., Li, W., Kamar, R. I., Liao, Y. a. & Hulet, R. G. Pairing and phase separation in a polarized Fermi gas. *Science* **311**, 503–505 (2006).
30. Nascimbène, S., Navon, N., Jiang, K. J., Chevy, F. & Salomon, C. Exploring the thermodynamics of a universal fermi gas. *Nature* **463**, 1057–1060 (2010).
31. Babaev, E. Vortices with fractional flux in two-gap superconductors and in extended Faddeev model. *Phys. Rev. Lett.* **89**, 067001 (2002).
32. Liu, W. V. & Wu, C. Atomic matter of nonzero-momentum Bose-Einstein condensation and orbital current order. *Phys. Rev. A* **74**, 013607 (2006).
33. Schneider, U. *et al.* Metallic and insulating phases of repulsively interacting fermions in a 3D optical lattice. *Science* **322**, 1520–1525 (2008).
34. Jordens, R., Strohmaier, N., Gunter, K., Moritz, H. & Esslinger, T. A Mott insulator of fermionic atoms in an optical lattice. *Nature* **455**, 204–207 (2008).
35. Greif, D., Uehlinger, T., Jotzu, G., Tarruell, L. & Esslinger, T. Short-range quantum magnetism of ultracold fermions in an optical lattice. *Science* **340**, 1307–1310 (2013).
36. Parker, C. V., Ha, L.-C. & Chin, C. Direct observation of effective ferromagnetic domains of cold atoms in a shaken optical lattice. *Nat. Phys.* **9**, 769–774 (2013).
37. Haldane, F. D. M. & Raghu, S. Possible realization of directional optical waveguides in photonic crystals with broken time-reversal symmetry. *Phys. Rev. Lett.* **100**, 013904 (2008).
38. Liu, W. V. Anomalous quantum mass flow of atoms in *p*-wave resonance. *Phys. Rev. A* **72**, 053613 (2005).
39. Shin, Y., Schunck, C. H., Schirotzek, A. & Ketterle, W. Tomographic rf spectroscopy of a trapped Fermi gas at unitarity. *Phys. Rev. Lett.* **99**, 090403 (2007).
40. Alba, E., Fernandez-Gonzalvo, X., Mur-Petit, J., Pachos, J. K. & Garcia-Ripoll, J. Seeing topological order in time-of-flight measurements. *Phys. Rev. Lett.* **107**, 235301 (2011).
41. Pachos, J. K., Alba, E., Lahtinen, V. & Garcia-Ripoll, J. Seeing Majorana fermions in time-of-flight images of staggered spinless fermions coupled by *s*-wave pairing. *Phys. Rev. A* **88**, 013622 (2013).
42. Zhao, E., Bray-Ali, N., Williams, C. J., Spielman, I. B. & Satija, I. I. Chern numbers hiding in time-of-flight images. *Phys. Rev. A* **84**, 063629 (2011).
43. Wang, L., Soluyanov, A. A. & Troyer, M. Proposal for direct measurement of topological invariants in optical lattices. *Phys. Rev. Lett.* **110**, 166802 (2013).
44. Price, H. M. & Cooper, N. R. Mapping the Berry curvature from semiclassical dynamics in optical lattices. *Phys. Rev. A* **85**, 033620 (2012).
45. Liu, X.-J., Law, K. T., Ng, T. K. & Lee, P. A. Detecting topological phases in cold atoms. *Phys. Rev. Lett.* **111**, 120402 (2013).
46. Li, X., Zhao, E. & Liu, W. V. Topological states in a ladder-like optical lattice containing ultracold atoms in higher orbital bands. *Nat. Commun.* **4**, 1523 (2013).
47. Sun, K., Liu, W. V., Hemmerich, A. & Das Sarma, S. Topological semimetal in a fermionic optical lattice. *Nat. Phys.* **8**, 67–70 (2012).
48. Bühler, A. *et al.* Majorana modes and *p*-wave superfluids for fermionic atoms in optical lattices. *Nat. Commun.* **5**, 4504 (2014).
49. Atala, M. *et al.* Direct measurement of the Zak phase in topological Bloch bands. *Nat. Phys.* **9**, 795–800 (2013).
50. Folling, S. *et al.* Direct observation of second-order atom tunnelling. *Nature* **448**, 1029–1032 (2007).

Acknowledgements

We thank Randy Hulet and Andrew Daley for helpful discussions. This work is supported by AFOSR (FA9550-12-1-0079), ARO (W911NF-11-1-0230), DARPA OLE Program through ARO and the Charles E. Kaufman Foundation of The Pittsburgh Foundation (B.L., X.L. and W.V.L.), the National Basic Research Program of China (Grant Nos. 2013CB921903 and 2012CB921300) and NSF of China (11274024 and 11334001 to B.W.), and Overseas Collaboration Program of NSF of China (11128407 to W.V.L., B.W.). X.L. acknowledges support by JQI-NSF-PFC, ARO-Atomtronics-MURI and AFOSR/JQI-MURI.

Author contributions

W.V.L. proposed the study of cross-band pairing during visits and discussions with B.W. X.L. and B.L. made breakthrough in theoretical ideas with inputs from B.W. and W.V.L. B.L. performed all calculations with X.L., under the supervision of W.V. L. and B.W. All authors worked on theoretical analysis and contributed in completing the paper.

Additional information

Supplementary Information accompanies this paper at <http://www.nature.com/naturecommunications>

Competing financial interests: The authors declare no competing financial interests.

Reprints and permission information is available online at <http://npng.nature.com/reprintsandpermissions/>

How to cite this article: Liu, B. *et al.* Chiral superfluidity with *p*-wave symmetry from an interacting *s*-wave atomic Fermi gas. *Nat. Commun.* 5:5064 doi: 10.1038/ncomms6064 (2014).